Product information LM 47 Long-Life Grease + MoS2



Description

High quality special grease. The MoS2 content provides the selected base grease with outstanding lubricity and high performance properties that normal grease simply does not have. During operation, a permanently adhering, ultra-thin molybdenum disulfide film forms on the sliding points. This film retains its lubricating action for a long time even after the grease supply completely fails. Extremely long lasting lubricity, transportable in central lubrication systems.

Properties

- increases operational reliability
- especially resistant to cold and hot water
- good corrosion protection
- can be delivered by centralized lubrication systems
- economical
- universal application
- high resistance to aging
- highest load-carrying capacity
- outstanding lubricating action
- distinctive high-pressure characteristics
- friction and wear reducing

Technical data

| l'echincal uala | |
|--|---------------------------------|
| Saponification type | Lithium |
| NLGI number | 2 |
| | DIN 51811 |
| Brief description | KPF2K-30 |
| | DIN 51502 |
| Worked penetration | 265-295 1/10 mm |
| | DIN ISO 2137 |
| Dropping point | >180 °C |
| | DIN ISO 2176 |
| Oil separation after 7 days at 40 °C | 8 % |
| - | DIN 51817 |
| Oil separation after 18 hours at 40 °C | 2,8 % DIN 51817 |
| | |
| Flow pressure at -30 °C | <1400 mbar DIN 51805 |
| Factor data data d | |
| Emcor corrosion class | 1/1 DIN 51802 |
| | |
| Copper corosion after 24 hours at 100 °C | 1 b DIN 51818 |
| | |
| Behavior in the presence of water | 0-90 DIN 51807 Teil 1 |
| E | |
| Four-ball tester material load/weld force | 2800/3200 N DIN 51350 Teil 4 |
| | |
| Four-ball tester wear/indentation diameter | 0,8 mm DIN 51350 Teil 5 |
| | |
| Base oil | mineral |

| 1 | in in the ful |
|---|---|
| | LIQU |
| | LM 47 |
| | aS ₂ -Langzeit |
| | Ó |
| | Parameteria andre andre Parale Lagenda da Parale Lagenda da Parameteria Antonio Parameteria Antonio |
| | |
| | |

Technical data

| Viscosity at 40 °C | 110 mm²/s ASTM D 7042-04 |
|--------------------|-----------------------------|
| Flash point | 220 °C DIN ISO 2592 |
| Pour point | -24 °C DIN ISO 3016 |

Areas of application

For general use under extreme conditions. For the assembly, maintenance and repair of motor vehicles, machine tools, construction machinery and presses. For high loaded bearings and joints, splined shafts, threads and guides. Suitable for constant velocity (CV) joints.

Application

As usual for grease. Follow the instructions of the bearing manufacturer.

Available pack sizes

| 100 g Tube plastic | 1987 D-RUS-UA |
|-------------------------|------------------------|
| 100 g Tube plastic | 3510 D |
| 400 g Cartridge plastic | 1842 D-NL-F-GR-ARAB |
| 400 g Cartridge plastic | 3520 D-GB-I-E-P |
| 400 g Cartridge plastic | 7574 D-RUS-UA |
| 1 kg Can sheet metal | 1843 D-NL-F-GR-ARAB |
| 1 kg Can sheet metal | 3530 D-GB-I-E-P |
| 5 kg Bucket plastic | 3540 D-GB |
| 25 kg Bucket plastic | 3550 D-GB |
| 180 kg Drum sheet metal | 2582 D-GB |

PI 26/12/01/2021

Product information LM 47 Long-Life Grease + MoS2

Our information is based on thorough research and may be considered reliable, although not legally binding.

