



TUNGREASE BS

Multi-Purpose EP-grease based on the OMC₂-Technology designed for long-term lubrication of the material pairing bronze/steel

- Product Description:** Very tacky EP-grease for long term lubrication. Especially developed for the lubrication of the material pairing bronze/steel.
- Performance:**
- Activates the self-lubrication properties of bronze based materials
 - Reduces vibrations, running and squeeze noise
 - Increases load carrying capacity
 - Reduces friction and wear
 - Good corrosion protection, aging and shear stability
 - Very good adhesion, resistant to spinning-off
 - Dirt and water repellent
 - Resistant to cold and hot water
 - Compatible with common seal materials
 - Fully compatible with Siemens Nylatron GSM
- Application:**
- For plain and rolling bearings, spline shafts, cardan and universal joints, spindles, guide-ways, cams, conveyor chains and gears
 - Specific for trapezoidal screws in the scissors lift table
- Method of use:** As it is usual for grease. Application of TUNGREASE CSH 2 on clean surfaces using e.g. TUNCLEAN 895.

| Product Name | Content | Article Number | Packing Unit |
|--------------|----------|-------------------|--------------|
| TUNGREASE BS | 1 kg can | 11A CF 13021g0010 | 1 pc |

Product Information



| Charachteristics | Value | Unit | Test Method |
|--------------------------------|---|-------------------------|--------------|
| Colour: | Light brown | - | visual |
| Density: | ca. 950 | kg/m ³ | DIN 51757 |
| Base oil: | synthetic | - | - |
| NLGI Class: | 1 | NLGI-Klasse | DIN 51818 |
| Thickener: | inorganic | - | - |
| Dropping Point: | none | °C | DIN ISO 2176 |
| Water Resistance: | 0-90 | rating | DIN 51807 |
| Steel-Corrosion, Emscor-Test: | 0-0 | rating | DIN 51802 |
| SRV, R700/60/2 BZ 10/ ST60: | <0,15 after running-in | friction coefficient | DBP 1648597 |
| Plastic Compatibility: | Compatibility with Siemens Nylatron GSM Home tested in the temperature range 0 C° up to 80 °C | | |

The above information is based on our general experience and knowledge at the time of printing. All provided data is considered guidance values that are based on the product composition, the specific use and application method. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary tests with the selected product. The product is continually improved and all technical data in this document will be adapted at any time without notice. Liabilities of any kind can not be derived from it. (51/2014)